

Galvanized Steel Wire Properties:
Elongation, Tensile Strength and Zinc Coating

diameter	tensile strength N/mm ²	elongat ion, %	zinc coatin g, g/m ²
2.1	1450	2.5	80
2.2	1,450	2.5	80
2.5	1,410	2.5	100
2.8	1,410	2.5	100
3.05	1,410	2.5	100
3.2	1,410	2.5	100
3.4	1,410	2.5	100
3.8	1,410	2.5	100
1.9	1,372		80
1.8	1,372		80
2.4	1,170		110
2.2	1170		110
2.6	1,370		90
2.8	1,370		90
3	1,370		100